

AIMTEK 694 (CM-64) Powder

| | |
|------------------------------------|--|
| Nominal Composition: | Co – Balance Cr – 28% W – 19.5% Ni – 5.0% V – 1% C – 0.85% |
| Properties: | Excellent High Temperature Wear and Oxidation Properties to 732°C Hard, dense coatings Inert Gas Atomized Powder |
| Industry Specifications: | GE B50A842 PWA694 PWA1314 |
| Particle Size Distribution: | -75/+45 μm -125/+45 μm |
| Density: | 4.7 g/cm ³ |

