

AIMTEK BRAZE ALLOY P829

Nominal Composition:	Ag – 82% Ga – 9% Pd – 9%
Melting Temperature:	Solidus (Flow point): 1553°F (845°C) Liquidus (Melt point): 1616°F (880°C)
Industry Specifications:	N/A
Common Applications:	Brazing Stainless Steel to Titanium
Forms Available:	Powder, Paste, Wire, Foil, Rings, Preforms

