

AIMTEK GOLD BRAZE ALLOY G82

| | |
|---------------------------------|---|
| Nominal Composition: | Au – 82% Ni-18% |
| Melting Temperature: | Solidus (Flow point): 1742°F (950°C) Liquidus (Melt point): 1742°F (950°C) |
| Industry Specifications: | AWS A5.8 BAu-4, BVAu-4 AMS4787 PWA698 B20L1A, B20L1C MSRR9500/118 GPS2451-1 Type II |
| Common Applications: | Stainless Steel, Nickel, Kovar, Inconel; Aircraft components, tubes, manifolds, fuel nozzles, vanes, vane rings |
| Forms Available: | Powder, Paste, Wire, Foil, Rings, Preforms |

