

AIMTEK SILVER BRAZE ALLOY S72

Nominal Composition:	Ag – 72% Cu – 28%
Melting Temperature:	Solidus (Flow point): 1435°F (779°C) Liquidus (Melt point): 1435°F (779°C)
Industry Specifications:	AWS A5.8 BAg-8, BVAg-8 MSRR9500/108
Common Applications:	Electrical Components, Copper, Nickel
Forms Available:	Powder, Paste, Wire, Foil, Rings, Preforms
Furnace Brazing Temperature:	1475-1525°F

