

## AIMTEK T-800 Powder

<b>Nominal Composition:</b>	<b>Co – Balance</b> <b>Mo – 28.5%</b> <b>Cr – 17.5%</b> <b>Si – 3.4%</b>
<b>Properties:</b>	Excellent Wear Properties to 816°C Good Hot Hardness, Oxidation, and Corrosion Properties Low Coefficient of Friction Inert Gas Atomized Powder
<b>Industry Specifications:</b>	GE B50TF190 Cl. A EMS 52432 XV PM 819-15 JA 13003
<b>Particle Size Distribution:</b>	-76/+45 μm -45/+16 μm
<b>Density:</b>	4.5 g/cm <sup>3</sup>

