

AIMTEK NI62 Brazing Powder and Paste

Nominal Composition:	Ni – Balance Cr – 15% B – 3.75%
Common Applications:	Jet engine parts; stainless steel components, nozzle assemblies, diffusion brazing, Silicon-free alloy, Eutectic
Industry Specifications:	AWS A5.8 BNi-9 PWA36962 B50TF207 MSRR9500/719
Particle Size Distribution:	Per specification
Forms Available:	Inert Gas Atomized Powder, Paste
Melting Range:	Solidus 1930°F (1054°C) Liquidus 1930°F (1054°C)
Recommended Brazing Temperature:	Vacuum 2075°F (1135°C)

