

## AIMTEK 694 (CM-64)

<b>Nominal Composition:</b>	Co – Balance Cr – 28% W + Mo – 19.5% Ni – 5.0% V – 1% C – 0.85% B – 0.05%
<b>Properties:</b>	Excellent High Temperature Wear and Oxidation Properties to 732°C Hard, dense coatings
<b>Industry Specifications:</b>	B50TF55 B50A842 PWA694 MSRR9500/226 MTS1087-1 DMR 34.070
<b>Forms Available:</b>	Weld Wire, Powder
<b>Density:</b>	4.7 g/cm <sup>3</sup>

